

# PRESSIZA 92

## PERFORMANCE GUIDE



### Features

- Thermal transfer printable polypropylene overlamine
- Excellent acid, chemical, oil and scuff resistance
- Designed for thermal transfer, hot foil stamp and Videojet® printability
- Specific ribbon testing required
- Ideal for bar code or other variable information applications

### Regulatory Compliance:

RoHS, RoHS2, REACH, TSCA, Toy Safety Standard ASTM F963, CEPA, CONEG, FDA 21 CFR 175.105, 21CFR177.1520(c) (1.1) & (3.1). California Proposition 65

### Face

Caliper 1.0 mil

### Adhesive

Thickness 0.3 +/- 10% inches

Peel Adhesion: Steel

13 oz/in 30 min conditioning

16 oz/in 24 hr conditioning

---

#### Temperature Ranges

Minimum Application 32°F (°C)

Service Ranges 0°F to 180°F (-18°C to 82°C)

### Roll Tolerances

Roll Length +/- 5%

Roll Width +/- 0.0625 in (1/16 in)

## Shelf Life

Two years when stored at 70°F and 50% relative humidity  
Rolls must be transported and stored on protected surfaces  
Use caution when placing or removing roll from mandrel



This information is confidential, and restricted for the internal use of RSI México customers for informative purposes, and can not be reproduced or communicated to third parties without our written authorization.

**TIJUANA:** (664) 215.0679

**PUEBLA:** (222) 225.6594

**HERMOSILLO:** (662) 369.7306

[comunicacion@rsimexico.com](mailto:comunicacion@rsimexico.com)

